

TECHNICAL DATA

FERICOAT -E 2600

Extreme Protective Epoxy Coat

Watertight, chemical and oil resistant

Two Component Solvent Free Epoxy Based Coating

FERICOAT – E2600 is a two-component, high-performance epoxy paint acceptable for either topside or in constant submersion duty. It provides excellent adhesion, chemical resistance, hardness and durability in harsh or abusive environments making it a favorite in many commercial applications. A government spec formula so you know you are getting the best!

Use **FERICOAT – E2600** wherever salt air and abusive weather conditions require an exceptionally hard, highly durable rust preventative epoxy barrier coating. It provides outstanding protection in virtually all interior and exterior applications. Intended for use on all metals, wood, fiberglass, aluminum, composite materials, concrete and masonry. Acceptable for use on hulls, bulkheads, decks, machinery, high traffic areas, control panels, cabinets, material handling equipment, gangways and ramps. Use it to refinish and protect water tanks and piping. Apply using brush, roller or spray (conventional, airless or electrostatic).

- A barrier coating acceptable for use above or below the waterline.
- Provides outstanding resistance to chemicals and spilled fuel.
- Produces an exceptionally hard scuff resistant finish.
- Provides superior adhesion, hardness and durability.
- Self leveling formula reduces brush and roller marks.
- Produces beautiful finish available in 100 colors plus clear.
- The hard, tough, durable finish offers unsurpassed stain, chemical, and abrasion resistance

FERICOAT – E2600 SPECIFICATION

FINISH	SEMI GLOSS
COLOUR	CLEAR, GREY, RED, GREEN AND CUSTOM COLOURS ARE AVAILABLE ON REQUEST.
VISCOSITY	THIXOTROPE
SPECIFIC GRAVITY	1.4 g/ml
VOLUME OF SOLIDS	80 %
COVERAGE	5 M ² /LIT @200 MICRON DFT
POT LIFE	8 HOURS @ 70 °C
TACK FREE	8 HOURS
RECOAT	22 HRS



TECHNICAL DATA

PACKING: Available as a two component kit. 1 US G /5 US G Kit.

RECOMMENDED PREPARATION: For best results remove old paint, loose scale, wax, oil and contaminates. Sand or scuff all surfaces prior to the application of any primer or coating. Fiberglass, aluminum, concrete, masonry and stainless steel, galvanized steel - strongly recommend the use of **FERICOAT – E2600** . All wood surfaces must be thoroughly cleaned and dry before the application of primer or coatings. Steel: All surfaces must be thoroughly dry and free of contaminates before the application of any primer or marine paint.

APPLICATION: **FERICOAT – E2600** supplied as two components, comprising part A and part B. Part B is added to Part A prior to the application and requires mechanical stirring. This mixture can be applied. Brush roller or good result also attained by spraying. Application of an undercoat will provide depth in color and durability to the finished surface. Use the largest Brush possible. Long flexible bristles are best and a good technique is the criss-cross method.

APPLY WITH BRUSH: Apply to the surface with a diagonal brushing action from the left to the right. This is then spread further with horizontal strokes before finally laying off with light vertical strokes. This results in any brush marks being able to flow out to give the best possible finish.

THIN AND CLEAN UP: Thinning not typically required. Use only with **ORGANIX** recommended thinner. Clean all equipment thoroughly with Lacquer Thinner or **ORGANIX** recommended one. Clean up with Lacquer Thinner **ORGANIX** recommended one.

*Use proper clothing, preferably minimum 60% cotton and equipment to protect skin from contact even though there are no specific antidotes for skin irritation. If it gets in eyes, should be washed with water or saline solution at least for ten minutes. Safety boots that are anti-static should cover at least the ankles. Natural ventilation is necessary during the application. Avoid spraying in high wind. Consult **ORGANIX** safety support for further assistance*

